Lead Foil Tape - 8 mil NV8LFT

PRODUCT DESCRIPTION

8 mil lead foil with an electrically conductive acrylic adhesive and release liner.

PRODUCT CONSTRUCTION

Substrate - 8 mil lead foil conforming to ASTM B29 and at a minimum to be 99.5% pure.

Adhesive - 3M electrically conductive acrylic adhesive.

TECHNICAL DATA	VALUE	TEST METHOD
Adhesive Thickness (mils)	2 +/- 0.5	VTP-1
Lead Foil Thickness (mils)	8 +/- 0.5	ASTM D1000
Total Thickness (mils) Nominal	10.5	ASTM D1000
Peel Strength (oz./inch) Min -24 hr. dwell	25	ASTM D1000
Resistance through tape (ohms/sq in) max.	20	MIL-STD-202
Volume Resistance (ohm-cm) max.	6.0	VTP-13

Note: The above are typical values and should **not** be used in writing specifications. The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representatives, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.

